

PROCESS		CHEMICALS						
PRIMER	TOPCOAT	GASOIL	GASOLINE 95	MOTOR OIL	COOLANT	SODIUM HYDROXIDE	HYDROCHLORIC ACID	SULFURIC ACID
-	PUR 840-G	0	5	0	0	0	0	0
-	SINT 740-G	0	5	0	1	0	0	0
-	SINT 740-S	0	5	0	0	1	0	1
PRIMAPOX 6041	ACRY-PUR 902-G	0	5	0	0	0	0	0
PRIMAPOX 6041	PUR 800-G	0	5	0	0	0	0	0
PRIMAPOX 6041	PUR 800-M	0	5	0	0	0	0	0
PRIMAPOX 6041	ACRY-PUR 901-G	0	5	0	0	0	0	0

VALUE	RESISTANCE LEVEL
0	NO CHANGE
1	VERY LIGHT
2	LIGHT
3	MODERATE
4	CONSIDERABLE
5	VERY INTENSE CHANGE