

PRIMAPUR 9141

2K Sealer / Podkład do zmiany koloru

PRODUKT

Podkład	PRIMAPUR 9141	
Utwardzacz	E-9006 szybki	4:1
	E-9005 standard	4:1
	E-9003 wolny	4:1
Rozcieńczalnik	PU74 standard	0-25%
	PU74L wolnu	0-25%

OPIS I WŁAŚCIWOŚCI

- Aplikacja w cienkie warstwie.
- Podkład do zmiany koloru bez matowania powierzchni.
- Do aplikacji mokro w mokro.

CECHY FIZYCZNE

Wygląd	Gładka powierzchnia	
Stopień połysku	Matt	
Ciężar właściwy	1,2 kg/l at 20°C	
Zawartość części stałych	54-58 % (weight)	39-44 % (volume)
Zawartość części stałych mieszanki bez rozcieńcz.	51-55 % (weight)	37-42 % (volume)
LZO mieszanki (10% rozcieńczalnika)	< 540g/l -2004/42/EC - IIA(j)(540)	
Grubość warstwy suchej	15-35 microns (1 coat)	
Wydajność teoretyczna z 1 lt przy grubości 1 µm	390-440 m ² /l	
Wydajność teoretyczna z 1 lt bez rozcieńczalnika przy grubości 1 µm	370-420 m ² /l	

SUBSTRATE AND SURFACE PREPARATION

	CLEANING	SANDING (OPTIONAL)	FINAL CLEANING
Old paints	DA93	P360/400	DA93



For other kind of substrates consult the Technical Service (SAT).



APPLICATION





T(°C)	SMALL SURFACE		LARGE SURFACE	
	Hardener	Thinner	Hardener	Thinner
18-25	E-9005	PU74/PU74L	E-9003/E-9005	PU74L
>25	E-9003	PU74L	E-9003	PU74L

	Mixing ratio Hardener (in volume)	4:1
	Electrostatic application (in volume)	---

	Application	% thinner (Vol.)	Viscosity - 20°C (Ford Cup 4)	Pressure (BAR)	Product Pressure (BAR)	Nozzle (mm)	Num. of Coats x µm dry
	Gravity feed spray gun	10%	28"-32"	2	---	1,3-1,4	1x20
	Pot life	4h					

DRYING

20° C

				
E-9003	13'	18'	20' - 24h	
E-9005	7'	14'	20' - 24h	
E-9006	6'	11'	15' - 24h	

The product develops its maximum properties after 15 days of air drying (ambient temperature 18-22°C) or after less time in higher temperatures.

SAFETY

- Follow instructions of product label.
- For more information check the Safety Data Sheet.
- Compliant with the National Statutory Regulation for Health and Safety at Work and Waste Disposal.



STORAGE

- Store the product in a ventilated place far from direct exposure to sunlight.
- Keep between +5°C and +30°C.

GUARANTEE

- One year in unopened original packaging.

*For any technical information contact with our Customer Attention Service or our Technical Department.
ROBERLO SA declines any responsibility due to an incorrect use of the product.*

